



Product Name	Properties			Main Components	T _g °C	Functional Group KOHmg/g	Epoxy Equivalent	Molecular Weight Mw	Regulation			
	Non Volatile Matter %	Viscosity mPa.s	Solvent / Monomer						China	Korea	Taiwan	TSCA
AS-3000	30±1	38,000~43,000* ¹	Toluene: Ethyl Acetate =9:1	BA	-36	-OH 8.5	—	650,000	Listed	—	Listed	—
ME-2000*	20±1	3,000~4,000* ¹	Ethyl Acetate	BA	-35	-COOH 20	—	600,000	Listed	Listed	Listed	Listed
W-116.3*	12.7±1	1,200~2,500* ²	Toluene: MEK =43:57	EA	-22	-COOH -OH 7.8 1.1	—	900,000	Listed	Listed	Listed	—
W-248E	30±1	38,000~43,000* ¹	Toluene: Ethyl Acetate =9:1	EA MMA	7	-OH 8.5	—	450,000	—	—	Listed	—
W-197C	35±1	45,000~50,000* ²	Toluene	EA MMA	18	-OH 8.5	—	400,000	—	—	Listed	—
PRE-COAT 200	20±1	10,000~15,000* ¹	Toluene: Ethyl Acetate =3:1	MMA	85	—	—	600,000	Listed	Listed	Listed	Listed
PANLONS-2012*	34.5±1	38,000~43,000* ¹	2-EHA	2-EHA	-60	-OH 6.5	—	900,000	—	—	Listed	—
KG-115	15±1	350~650* ²	MEK	BA	-4	—	2900	650,000	Listed	Listed	Listed	—

*Produced after orders received

Temperature / *¹20°C、*²25°C

Note: These values are for reference only.